

Differential Pressure (Delta P) Final Report

Test Article: HPRFSC
 Purchase Order: ASB-Tang-PPE-Testing
 Study Number: 1329267-S01
 Study Received Date: 07 Aug 2020
 Testing Facility: Nelson Laboratories, LLC
 6280 S. Redwood Rd.
 Salt Lake City, UT 84123 U.S.A.
 Test Procedure(s): Standard Test Protocol (STP) Number: STP0004 Rev 18
 Deviation(s): None

Summary: The Delta P test is performed to determine the breathability of test articles by measuring the differential air pressure on either side of the test article using a manometer, at a constant flow rate. The Delta P test complies with EN 14683:2019, Annex C and ASTM F2100-19.

All test method acceptance criteria were met. Testing was performed in compliance with US FDA good manufacturing practice (GMP) regulations 21 CFR Parts 210, 211 and 820.

Test Side: Inside
 Delta P Flow Rate: 8 Liters per minute (L/min)
 Conditioning Parameters: 85 ± 5% relative humidity (RH) and 21 ± 5°C for a minimum of 4 hours
 Test Article Dimensions: ~174 mm x ~154 mm

Results:

Test Article Number	Delta P (mm H ₂ O/cm ²)	Delta P (Pa/cm ²)
1	4.1	40.2
2	4.3	41.7
3	4.2	40.9
4	4.4	43.3
5	4.0	39.5



Trang Truong electronically approved for
Study Director

James Luskin

15 Aug 2020 01:14 (+00:00)
Study Completion Date and Time